

Material Code	Remanence		Coercivity		Intrinsic Coercivity		Max. Energy Product (BH)max	
	Br		Hcb		Hcj		KJ/m3	MGOe
	KG	mT	KA/m	KOe	KA/m	KOe		
YX16	7.5 - 8.8	750 - 880	597 +/- 40	7.5 +/- 0.5	≥1989	≥25	127 +/- 16	16 +/- 2
YX18	8.0 - 9.3	800 - 930	637 +/- 40	8 +/- 0.5	≥1432	≥18	143 +/- 16	18 +/- 2
YX20	8.5 - 9.8	850 - 980	637 +/- 40	8 +/- 0.5	≥1273	≥16	159 +/- 16	20 +/- 2
YXT18	9.0 - 10.3	900 - 1030	637 +/- 40	8 +/- 0.5	≥1194	≥15	143 +/- 16	18 +/- 2
YX22A	9.0 - 10.3	900 - 1030	653 +/- 40	8.2 +/- 0.5	≥1989	≥25	175 +/- 16	22 +/- 2
YX22B	9.0 - 10.3	900 - 1030	635 +/- 40	8.2 +/- 0.5	≥1432	≥18	175 +/- 16	22 +/- 2
YX24	9.5 - 10.8	950 - 1080	676 +/- 40	8.5 +/- 0.5	≥1432	≥18	191 +/- 16	24 +/- 2
YX26A	10.0 - 11.3	1000 - 1130	716 +/- 40	9.0 +/- 0.5	≥1194	≥15	207 +/- 16	26 +/- 2
YX26B	10.0 - 11.3	1000 - 1130	716 +/- 40	9.0 +/- 0.5	≥796	≥10	207 +/- 16	26 +/- 2
YX27	10.0 - 11.0	1000 - 1100	357 - 516	4.5 - 6.5	413 - 556	5.2 - 7.0	183 - 223	26 +/- 2
YX30	11.0 - 12.0	1100 - 1200	438 - 517	5.5 - 6.5	454 - 597	5.7 - 7.5	239 +/- 16	30 +/- 2