

No	Tempt.Coefficient α Br % /°C	Density D g/cm3	Curie Temp. Tc °C	Recoil Permeability μ rec	Operating Temp. °C / F	Product Type
1	-0.05	8.0 - 8.2	700 - 750	1.1	250 / 482	YX16, YX18, YX20
2	-0.01	8.3 - 8.5	≥ 800	1.1	250 / 482	YXT18
3	-0.03	8.3 - 8.5	≥ 800	1.1	250 / 482	YX22A, YX22B
4						YX26A, YX26B
5						YX24, YX27, YX30